

Neroline 9000

Product Description

Epoxy phenolic resin suitably pigmented & separately packed clear polyamine adduct solution as hardener.

Recommended Use

Neroline 9000 is a two-pack high build epoxy phenolic topcoat. This product is designed to use as a topcoat for tank lining paint systems, concrete bridges, MS structures. It has excellent resistance against highly corrosive and humid atmosphere.

PHYSICAL PROPERTIES

Colour	Grey
Finish	Matt to Eggshell
Temperature Resistance (Dry)	Non-Continuous: 200°C Continuous: 120°C

Product Features

Self-Priming	Excellent resistance to oils and chemicals
Excellent resistance to highly corrosive & humid conditions	Excellent resistance to water and sea water
	Tough, hard and high abrasion resistant

Product Details

Volume solids



65 ± 3%

DFT/Coat



75 - 125 μ

VOC (EPA Method 24)



304 gm/Lit

Theoretical Coverage/Coat



5.20 – 8.6 m²/litr.

Pack size

20 Ltr.: (16 Ltr. - Part A + 4 Ltr. Part B = 20 Ltr. Mix).

Drying at 30°C & 65% RH

Surface (Touch) Dry	2 - 3 Hrs
Hard Dry	10 - 12 Hrs
Full Cure	7 Days

Overcoating Interval

Temperature	20°C	30°C	40°C
Min	8 Hrs.	6 Hrs.	5 Hrs.
Max	5 days	5 days	5 days

The drying time varies with respect to changes in temperature, humidity & DFT.

After max. overcoating interval the surface should be roughened prior to application of subsequent coat.

Neroline 9000

Surface Preparation

For Newly Build:

Abrasive blasting to min. Sa 2½ (ISO 8501-1) / SSPC SP 10 – Stainless steel, aluminium and other non-ferrous metals use non-metallic blast media like garnet. Remove sharp profile, without blank spots, remove dust & loose particles.

For Old Surface / Maintenance and Repair:

Abrasive blasting to min. Sa 2 (ISO 8501-1) / SSPC SP 6, Water jetting to min Wa 2 (ISO 8501-4). Areas also can be cleaned by power tool to St 3 provided the surface is roughened and not polished.

Surface Cleanliness:

- Remove oil, grease and other contaminants by suitable cleaner
- Remove dust, blast media and loose particles
- Surface should be clean & dry before application of coating

Application Instructions

Stir the Comp. A until homogenous. If settling is observed in the component A, loosen the settled material & mix it with the help of pneumatic stirrer. Mix component B gradually into component A in the specified ratio under continuous stirring till homogeneous. Use Nerolac Epoxy thinner as recommended.

Mixing Ratio by Volume

Component A : Component B

4 : 1

Pot Life

Up to 2 Hrs. at 30°C

Curing Mechanism

Solvent release and chemical reaction between two components

Thinner Consumption

Airless Spray

0 – 10%

Brush

0 – 10%

Conventional Spray

5 – 20%

The product can be applied by:

- Airless Spray – Nozzle pressure: 175 bar [2500 psi] Nozzle orifice: 0.017–0.021"
- Conventional Spray
- Brush

During application following precautions should be taken:

- Relative humidity must be below 85% during application as well as during curing
- Do not allow material to remain in hoses, gun or spray equipment
- Clean all equipment with recommended thinner immediately after completion of job.

Neroline 9000

Environmental Conditions

Surface temperature must be 3°C above Dew Point to prevent condensation.

Air	5 – 40°C
Surface	5 – 50°C
Relative Humidity	Below 85%

Storage & Shelf Life

12 months under normal storage condition in original sealed containers at 30°C.

Heavy pigments will have a natural tendency to settle down over time. Mix uniformly with heavy duty stirrer prior to usage. Hard settling may occur if stored above the recommended storage temperature.

Safety Precautions

Please refer to the Material Safety Data Sheet.

Product Compatibility

Suitable to be coated over Zinc Rich and Epoxy primers

Suitable Top coats: - Epoxy, PU.

Special Notes

Thinner consumption may vary depending upon site conditions. Practical covering capacity depends on application techniques, ambient conditions, wastage, surface condition etc. The drying time and overcoating interval vary with respect to change in temperature, humidity, film thickness, ventilation, thinner intake etc.

Outdoor exposure in sunlight or exposure to elevated temperatures may result in chalking / discoloration in all epoxies. However, it does not affect the anti-corrosive performance.

The coating should be fully cured till 7 days prior to exposure to in service conditions.

DISCLAIMER:

KANSAI NEROLAC PAINTS Ltd. (KNPL) warrants that all products are free from any defects of manufacture and comply with the specification given in their respective technical data sheet. No warranty can be given as to the results of use because conditions of use, such as site conditions, surface preparations, workmanship, weather, structural issues and other factors are beyond the control of **NEROLAC**. Purchaser agrees to seek the advice of qualified professionals to carry out tests and take trials to determine the suitability of products for their intended purpose prior to full scale use of KNPL products and assumes all risks.

The company does not assume any liability for unsatisfactory results, arising from the use of our products. Purchaser's sole liability is limited to replacement of product or refund of the purchase price paid if any product proven defective. No other warranties express or implied, shall apply including any warranty of merchantability or fitness for particular purpose.

KNPL shall not be liable for any consequential damages arising from the use of our products for unsatisfactory results. The information supplied in this data sheet is based on our experience through extensive research and is given in good faith in order to help prospective users. We reserve the right to update the information provided in our technical data sheet at any time without prior notice within the scope of technical progress or new developments.

PN - 1063586

Issue Date :- Oct 25